



The Cryogenic Tensile Properties of an Extruded Aluminum-Beryllium Alloy

W.R. Gamwell

Marshall Space Flight Center, Marshall Space Flight Center, Alabama



The NASA STI Program Office...in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) Program Office plays a key part in helping NASA maintain this important role.

The NASA STI Program Office is operated by Langley Research Center, the lead center for NASA's scientific and technical information. The NASA STI Program Office provides access to the NASA STI Database, the largest collection of aeronautical and space science STI in the world. The Program Office is also NASA's institutional mechanism for disseminating the results of its research and development activities. These results are published by NASA in the NASA STI Report Series, which includes the following report types:


- **TECHNICAL PUBLICATION.** Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA's counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- **TECHNICAL MEMORANDUM.** Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- **CONTRACTOR REPORT.** Scientific and technical findings by NASA-sponsored contractors and grantees.

- **CONFERENCE PUBLICATION.** Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- **SPECIAL PUBLICATION.** Scientific, technical, or historical information from NASA programs, projects, and mission, often concerned with subjects having substantial public interest.
- **TECHNICAL TRANSLATION.** English-language translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services that complement the STI Program Office's diverse offerings include creating custom thesauri, building customized databases, organizing and publishing research results...even providing videos.

For more information about the NASA STI Program Office, see the following:

- Access the NASA STI Program Home Page at <http://www.sti.nasa.gov>
- E-mail your question via the Internet to help@sti.nasa.gov
- Fax your question to the NASA Access Help Desk at (301) 621-0134
- Telephone the NASA Access Help Desk at (301) 621-0390
- Write to:
NASA Access Help Desk
NASA Center for AeroSpace Information
7121 Standard Drive
Hanover, MD 21076-1320



The Cryogenic Tensile Properties of an Extruded Aluminum-Beryllium Alloy

W.R. Gamwell

Marshall Space Flight Center, Marshall Space Flight Center, Alabama

National Aeronautics and
Space Administration

Marshall Space Flight Center • MSFC, Alabama 35812

Acknowledgments

The author would like to acknowledge the Metallic Materials and Processes Group support contractors for performing the mechanical tests, and Tina Malone for coordinating the testing in the author's absence, and for reviewing the manuscript and the statistical analyses and results.

Available from:

NASA Center for AeroSpace Information
7121 Standard Drive
Hanover, MD 21076-1320
(301) 621-0390

National Technical Information Service
5285 Port Royal Road
Springfield, VA 22161
(703) 487-4650

TABLE OF CONTENTS

1. INTRODUCTION	1
2. EXPERIMENTAL PROCEDURE	2
3. RESULTS	5
4. CONCLUSIONS	14
REFERENCES	15

LIST OF FIGURES

1.	Tensile specimen	2
2.	Extruded AlBeMet162 test specimen layout	3
3.	AlBeMet162 with (a) ultimate tensile strength (MPa) versus temperature (°C) and (b) ultimate tensile strength (ksi) versus temperature (°F)	7
4.	AlBeMet162 with (a) yield strength (MPa) versus temperature (°C) and (b) yield strength (ksi) versus temperature (°F)	8
5.	AlBeMet162 percent elongation versus (a) temperature (°C) and (b) temperature (°F)	9
6.	AlBeMet162 design properties for ultimate tensile strength and yield strength versus (a) temperature (°C) and (b) temperature (°F)	12
7.	AlBeMet162 design properties for percent elongation versus (a) temperature (°C) and (b) temperature (°F)	13

LIST OF TABLES

1.	AlBeMet162 tensile data at room temperature, -195.5 and -252.8 °C	5
2.	AlBeMet162 tensile data at room temperature, -320 and -423 °F	6
3.	Mechanical property mean data summary	10
4.	ANOVA results	10

LIST OF ACRONYMS, ABBREVIATIONS, AND SYMBOLS

45	45° (orientation)
Al	aluminum
ANOVA	analysis of variance
Be	beryllium
L	longitudinal (orientation)
L–T	long-transverse (orientation)
T	material thickness

TECHNICAL MEMORANDUM

THE CRYOGENIC TENSILE PROPERTIES OF AN EXTRUDED ALUMINUM-BERYLLIUM ALLOY

1. INTRODUCTION


Aluminum (Al)-beryllium (Be) materials have been around for some time, beginning with the material developed in the 1960s by Lockheed called "Lockalloy."¹ Interest in their use waned in the 1970s and the materials became unavailable. In the past decade, due to the desirable performance characteristics of this family of composite materials for aerospace applications, new alloys have been developed with improved mechanical properties, along with improved processing techniques and process controls for their production. Al-Be materials are available in the form of extrusions, rolled plate, forgings, and most recently, near-net-shaped investment castings.

Desirable characteristics of Al-Be materials include lightweight, dimensional stability, stiffness, good vibration-damping characteristics, low coefficient of thermal expansion, and workability.¹ These materials are 3.5 times stiffer and 22-percent lighter than conventional Al alloys. Their use is attractive for weight-critical structural applications such as advanced electro-optical systems; advanced sensor and guidance components for flight and satellite systems; components for lightweight, high-performance aircraft engines; and structural components for helicopters. As these materials become more highly used in aerospace programs, mechanical properties at liquid hydrogen temperatures will be needed for structural analyses. These properties are currently not available for these families of alloys.

AlBeMet162 is an Al-Be extruded alloy that was developed by the Brush Wellman Company.¹ It is currently being used on the telescope for the Next-Generation Space Telescope program for its desirable properties. The cryogenic tensile properties for this alloy were evaluated for Goddard Space Flight Center.

2. EXPERIMENTAL PROCEDURE

Tensile specimens were obtained from the Brush Wellman Company and fabricated per figure 1 from extruded AlBeMet162 material per SAE-AMS7912, "Aluminum-Beryllium Alloy, Extrusions."² The extrusion used to extract the specimens was approximately 2 by 8 by 35 in. Test specimens were extracted from the extrusion in the longitudinal (L), long-transverse (L-T), and 45° (45) orientations, and from the T/6, T/2, and 5T/6 locations (T = material thickness) along the length of the extrusion as shown in figure 2.



Notes:

1. The ends of the reduced section shall differ by not more than 0.002 in: there must be a gradual taper in width from the ends to the center (0.005 in max)
2. Holes must be on centerline of reduced section within ±0.002 in
3. Break all edges 0.005 in max
4. Do not undercut 0.005 in rad
5. These are final part size dimensions in inches.

Figure 1. Tensile specimen.

Twelve specimens were extracted from the T/6 location along the length of the extrusion—five with the L orientation, five with the L–T orientation, and two with the 45° orientation. Twelve specimens were extracted from the T/2 location along the length of the extrusion—five with the L orientation, five with the L–T orientation, and two with the 45° orientation. Eleven specimens were extracted from the 5T/6 location of the extrusion—five with the L orientation, five with the L–T orientation, and one with the 45° orientation (fig. 2). The different orientations were tested to determine whether a significant difference in the mechanical properties was discernable at cryogenic temperatures.

Tensile testing was performed at room temperature, at –195.5 °C (–320 °F) and at –252.8 °C (–423 °F). Room-temperature testing was performed to verify mechanical properties' conformance of the material to those specified in AMS7912. Cryogenic testing was performed to characterize the material properties; i.e., ultimate tensile strength, yield strength, percent elongation, and modulus, at the subject temperatures.

3. RESULTS


Mechanical property results are shown in tables 1 and 2 and figures 3–5. The means of the ultimate tensile and yield strengths and percent elongation for each temperature and specimen orientation are shown in table 3. Analysis of variance (ANOVA) results are shown in table 4. ANOVA was conducted for comparison of differences between the longitudinal and transverse specimens at -195.5°C (-320°F) and -252.8°C (-423°F), and for comparison of differences between properties of the same specimen orientation at different temperatures.

Table 1. AlBeMet162 tensile data at room temperature, -195.5 and -252.8°C .


Other ID No.	Orientation	Test Type	Temp. ($^{\circ}\text{C}$)	0.2% Yield Strength (MPa)	Ultimate Tensile Strength (MPa)	Elastic Modulus (GPa)	1-in Elongation (%)	Plastic Elongation (%)	Total Elongation (%)
T6L1	L	Tensile	21	331.8	451.3	175.8	–	8.1	8.2
T2L5	L	Tensile	21	316.5	432.0	172.4	–	7.4	7.6
5T6L3	L	Tensile	21	317.8	426.8	180.0	–	6.3	6.5
5T6T4	T	Tensile	21	317.5	377.2	155.8	–	2.3	2.5
T6T5	T	Tensile	21	318.2	389.9	171.7	–	2.4	2.6
T2T3	T	Tensile	21	312.3	372.3	165.5	–	2.4	2.6
T6–45–1	45	Tensile	-195.5	310.3	456.4	237.9	2.7	2.5	2.7
T2–45–1	45	Tensile	-195.5	327.5	492.3	175.1	3.8	3.9	4.2
T6L2	L	Tensile	-195.5	362.7	530.2	176.5	3.1	3.3	3.6
T6L5	L	Tensile	-195.5	366.1	533.7	180.0	3.4	3.3	3.6
T2L3	L	Tensile	-195.5	347.5	515.0	216.5	3.1	3.1	3.3
5T6L1	L	Tensile	-195.5	355.1	475.7	186.8	2.9	1.9	2.2
5T6L4	L	Tensile	-195.5	384.0	427.5	188.2	0.6	0.8	1
T2T4	T	Tensile	-195.5	342.0	452.3	161.3	1.7	1.5	1.8
5T6T2	T	Tensile	-195.5	347.5	439.9	183.4	1.5	1.4	1.6
5T6T5	T	Tensile	-195.5	347.5	464.0	171.7	1.7	1.7	1.9
T6T3	T	Tensile	-195.5	346.8	475.7	189.6	2.0	1.8	2
T2T1	T	Tensile	-195.5	333.7	417.1	169.6	1.4	0.9	1.1
T2–45–2	45	Tensile	-252.8	439.2	536.4	176.5	1.5	1.06	1.36
T6–45–2	45	Tensile	-252.8	460.6	572.3	157.9	0.7	1.26	1.63
5T6–45–1	45	Tensile	-252.8	392.3	521.2	201.3	1.2	1.58	1.83
T6L3	L	Tensile	-252.8	474.4	537.1	175.1	–	0.62	0.92
T2L1	L	Tensile	-252.8	443.3	517.8	168.2	0.5	0.73	1.03
T2L4	L	Tensile	-252.8	450.2	578.5	221.3	1.3	1.44	1.7
5T6L2	L	Tensile	-252.8	440.6	528.8	200.6	0.8	0.88	1.15
5T6L5	L	Tensile	-252.8	477.1	554.3	159.3	1.1	0.92	1.26
T6L4	L	Tensile	-252.8	404.7	577.8	157.2	2.6	2.95	3.15
T2L2	L	Tensile	-252.8	462.6	553.6	184.1	1.1	1.05	1.3
T6T4	T	Tensile	-252.8	426.8	501.2	176.5	0.8	0.69	0.96
T2T5	T	Tensile	-252.8	433.7	512.3	158.6	–	0.64	0.96
5T6T3	T	Tensile	-252.8	433.0	521.9	199.3	0.8	0.75	1
T6T1	T	Tensile	-252.8	434.4	539.9	188.2	1.3	0.89	1.17
T2T2	T	Tensile	-252.8	422.0	523.3	204.8	1.3	0.95	1.21
5T6T1	T	Tensile	-252.8	421.3	496.4	159.3	0.7	0.88	1.08
T6T2	T	Tensile	-252.8	405.4	499.9	195.8	0.8	0.75	0.995

Table 2. AlBeMet162 tensile data at room temperature, –320 and –423 °F.

Other ID NO.	Orientation	Test Type	Temp. (°F)	0.2% Yield Strength (ksi)	Ultimate Tensile Strength (ksi)	Elastic Modulus (Msi)	1-in Elongation (%)	Plastic Elongation (%)	Total Elongation (%)
T6L1	L	Tensile	70	48.1	65.5	25.5	–	8.1	8.2
T2L5	L	Tensile	70	45.9	62.7	25.0	–	7.4	7.6
5T6L3	L	Tensile	70	46.1	61.9	26.1	–	6.3	6.5
5T6T4	T	Tensile	70	46.1	54.7	22.6	–	2.3	2.5
T6T5	T	Tensile	70	46.2	56.6	24.9	–	2.4	2.6
T2T3	T	Tensile	70	45.3	54.0	24.0	–	2.4	2.6
T6–45–1	45	Tensile	–320	45.0	66.2	34.5	2.7	2.5	2.7
T2–45–1	45	Tensile	–320	47.5	71.4	25.4	3.8	3.9	4.2
T6L2	L	Tensile	–320	52.6	76.9	25.6	3.1	3.3	3.6
T6L5	L	Tensile	–320	53.1	77.4	26.1	3.4	3.3	3.6
T2L3	L	Tensile	–320	50.4	74.7	31.4	3.1	3.1	3.3
5T6L1	L	Tensile	–320	51.5	69.0	27.1	2.9	1.9	2.2
5T6L4	L	Tensile	–320	55.7	62.0	27.3	0.6	0.8	1
T2T4	T	Tensile	–320	49.6	65.6	23.4	1.7	1.5	1.8
5T6T2	T	Tensile	–320	50.4	63.8	26.6	1.5	1.4	1.6
5T6T5	T	Tensile	–320	50.4	67.3	24.9	1.7	1.7	1.9
T6T3	T	Tensile	–320	50.3	69.0	27.5	2.0	1.8	2
T2T1	T	Tensile	–320	48.4	60.5	24.6	1.4	0.9	1.1
T2–45–2	45	Tensile	–423	63.7	77.8	25.6	1.5	1.06	1.36
T6–45–2	45	Tensile	–423	66.8	83.0	22.9	0.7	1.26	1.63
5T6–45–1	45	Tensile	–423	56.9	75.6	29.2	1.2	1.58	1.83
T6L3	L	Tensile	–423	68.8	77.9	25.4	–	0.62	0.92
T2L1	L	Tensile	–423	64.3	75.1	24.4	0.5	0.73	1.03
T2L4	L	Tensile	–423	65.3	83.9	32.1	1.3	1.44	1.7
5T6L2	L	Tensile	–423	63.9	76.7	29.1	0.8	0.88	1.15
5T6L5	L	Tensile	–423	69.2	80.4	23.1	1.1	0.92	1.26
T6L4	L	Tensile	–423	58.7	83.8	22.8	2.6	2.95	3.15
T2L2	L	Tensile	–423	67.1	80.3	26.7	1.1	1.05	1.3
T6T4	T	Tensile	–423	61.9	72.7	25.6	0.8	0.69	0.96
T2T5	T	Tensile	–423	62.9	74.3	23.0	–	0.64	0.96
5T6T3	T	Tensile	–423	62.8	75.7	28.9	0.8	0.75	1
T6T1	T	Tensile	–423	63.0	78.3	27.3	1.3	0.89	1.17
T2T2	T	Tensile	–423	61.2	75.9	29.7	1.3	0.95	1.21
5T6T1	T	Tensile	–423	61.1	72.0	23.1	0.7	0.88	1.08
T6T2	T	Tensile	–423	58.8	72.5	28.4	0.8	0.75	0.995




(a)




(b)

Figure 3. AlBeMet162 with (a) ultimate tensile strength (MPa) versus temperature (°C) and (b) ultimate tensile strength (ksi) versus temperature (°F).




(a)




(b)

Figure 4. AlBeMet162 with (a) yield strength (MPa) versus temperature (°C) and (b) yield strength (ksi) versus temperature (°F).



(a)



(b)

Figure 5. AlBeMet162 percent elongation versus (a) temperature (°C) and (b) temperature (°F).

Table 3. Mechanical property mean data summary.

Temperature °C (°F)	Orientation	No. Specimens	Ultimate Tensile Strength		Yield Strength		Elongation (%)
			MPa	(ksi)	MPa	(ksi)	
-252.8 (-423)	L	7	549.5	(79.7)	450.2	(65.3)	1.50
-252.8 (-423)	T	7	513.7	(74.5)	425.4	(61.7)	1.05
-195.5 (-320)	L	5	496.4	(72.0)	363.4	(52.7)	2.70
-195.5 (-320)	T	5	449.5	(65.2)	343.4	(49.8)	1.70
21 (70)	L	3	437.1	(63.4)	322.0	(46.7)	6.40
21 (70)	T	3	379.9	(55.1)	316.5	(45.9)	2.60

Table 4. ANOVA results.

Treatment	Temperature °C (°F)		α	Results
UTS-L/UTS-T	-252.8/-252.8	(-423/-423)	0.05	The means are statistically different
YS-L/YS-T	-252.8/-252.8	(-423/-423)	0.05	The means are statistically different
%e-L/%e-T	-252.8/-252.8	(-423/-423)	0.05	Cannot distinguish a difference in means at this α level
UTS-L/UTS-T	-195.5/-195.5	(-320/-320)	0.05	Cannot distinguish a difference in means at this α level
YS-L/YS-T	-195.5/-195.5	(-320/-320)	0.05	The means are statistically different
%e-L/%e-T	-195.5/-195.5	(-320/-320)	0.05	Cannot distinguish a difference in means at this α level
UTS-L/UTS-T	21/21	(70/70)	0.05	The means are statistically different
YS-L/YS-T	21/21	(70/70)	0.05	Cannot distinguish a difference in means at this α level
%e-L/%e-T	21/21	(70/70)	0.05	The means are statistically different
UTS-L/UTS-L	-252.8/-195.5	(-423/-320)	0.05	The means are statistically different
UTS-L/UTS-T	-252.8/-195.5	(-423/-320)	0.05	The means are statistically different
YS-L/YS-L	-252.8/-195.5	(-423/-320)	0.05	The means are statistically different
YS-L/YS-T	-252.8/-195.5	(-423/-320)	0.05	The means are statistically different
%e-L/%e-L	-252.8/-195.5	(-423/-320)	0.05	The means are statistically different
%e-L/%e-T	-252.8/-195.5	(-423/-320)	0.05	The means are statistically different
UTS-L/UTS-L	-195.5/21	(-320/70)	0.05	Cannot distinguish a difference in means at this α level
UTS-L/UTS-T	-195.5/21	(-320/70)	0.05	The means are statistically different
YS-L/YS-L	-195.5/21	(-320/70)	0.05	The means are statistically different
YS-L/YS-T	-195.5/21	(-320/70)	0.05	The means are statistically different
%e-L/%e-L	-195.5/21	(-320/70)	0.05	The means are statistically different
%e-L/%e-T	-195.5/21	(-320/70)	0.05	The means are statistically different

LEGEND:

UTS = Ultimate tensile strength

YS = Yield strength

%e = Percent elongation

L = Longitudinal specimen

T = Transverse specimen

Mechanical properties at room temperature met the requirements of specification AMS7912 for the ultimate tensile and yield strengths for both longitudinal and transverse specimens. The elongation met the specification requirement for the transverse specimens, but was below the requirement for two of the three longitudinal specimens. ANOVA performed on the room-temperature data showed that the ultimate tensile strength and percent elongation between the longitudinal and transverse specimen orientations are distinguishable, whereas the yield strength between these two orientations was not distinguishable statistically. This was consistent with the properties listed in the specification for these two orientations.


The ultimate tensile and yield strength at $-195.5\text{ }^{\circ}\text{C}$ ($-320\text{ }^{\circ}\text{F}$) were increased over the room-temperature mechanical properties. ANOVA performed on the $-195.5\text{ }^{\circ}\text{C}$ ($-320\text{ }^{\circ}\text{F}$) data showed the ultimate tensile strength and percent elongation were not distinguishably different between the longitudinal and transverse orientations, but the yield strengths were distinguishable statistically. ANOVA showed the $-195.5\text{ }^{\circ}\text{C}$ ($-320\text{ }^{\circ}\text{F}$) properties were distinguishably different from the room-temperature properties in all cases except for the ultimate tensile strength–L orientation. For this case, the difference in means between $-195.5\text{ }^{\circ}\text{C}$ ($-320\text{ }^{\circ}\text{F}$) and $21\text{ }^{\circ}\text{C}$ ($70\text{ }^{\circ}\text{F}$) was large, and one would expect a statistical difference in means. The reason the means were not distinguishable was because of the extremely large variance in the $-195.5\text{ }^{\circ}\text{C}$ ($-320\text{ }^{\circ}\text{F}$) data.

The ultimate tensile and yield strengths at $-252.8\text{ }^{\circ}\text{C}$ ($-423\text{ }^{\circ}\text{F}$) were increased over the $-195.5\text{ }^{\circ}\text{C}$ ($-320\text{ }^{\circ}\text{F}$) and room-temperature mechanical properties. ANOVA performed on the $-252.8\text{ }^{\circ}\text{C}$ ($-423\text{ }^{\circ}\text{F}$) data showed the ultimate tensile and yield strengths were distinguishably different between the longitudinal and transverse orientations, but the percent elongation was not distinguishable statistically. ANOVA showed the $-252.8\text{ }^{\circ}\text{C}$ ($-423\text{ }^{\circ}\text{F}$) properties were distinguishably different from the $-195.5\text{ }^{\circ}\text{C}$ ($-320\text{ }^{\circ}\text{F}$) properties in all cases.


Design values for the ultimate tensile and yield strengths versus temperature were generated from the mechanical property data and are shown in figure 6. The design properties are presented as ratios of the minimum cryogenic temperature ultimate tensile and yield strength values obtained during testing divided by the AMS7912 transverse room-temperature property. Figure 6 data represent lower bound properties for both the longitudinal and transverse directions. They do not represent A- or B-basis properties. To obtain cryogenic properties, multiply the AMS7912 room-temperature ultimate tensile or yield strength value by the percentage shown in figure 6.

Design values for percent elongation are shown in figure 7. These values are based on the AMS7912 value for room temperature, and on the minimum values obtained during testing at $-195.5\text{ }^{\circ}\text{C}$ ($-320\text{ }^{\circ}\text{F}$) and $-252.8\text{ }^{\circ}\text{C}$ ($-423\text{ }^{\circ}\text{F}$). Note the poor ductility at $-195.5\text{ }^{\circ}\text{C}$ ($-320\text{ }^{\circ}\text{F}$) and $-252.8\text{ }^{\circ}\text{C}$ ($-423\text{ }^{\circ}\text{F}$).

Modulus values shown in tables 1 and 2 are typical values based on tensile test results.




(a)




(b)

Figure 6. AlBeMet162 design properties for ultimate tensile strength and yield strength versus (a) temperature (°C) and (b) temperature (°F).



(a)



(b)

Figure 7. AlBeMet162 design properties for percent elongation versus (a) temperature (°C) and (b) temperature (°F).

4. CONCLUSIONS

The ultimate tensile and yield strengths for extruded AlBeMet162 material increase with decreasing temperature. The percent elongation for extruded AlBeMet162 material decreases with decreasing temperature.

At cryogenic temperatures, the ultimate tensile and yield strengths are higher in the longitudinal direction than the long-transverse direction. This is consistent with the room-temperature mechanical property data of AMS7912. At cryogenic temperatures, it is not possible to distinguish a difference in percent elongation between the longitudinal and long-transverse directions, whereas there is a difference in percent elongation at room temperature per AMS7912.

The ultimate tensile and yield strengths at $-252.8\text{ }^{\circ}\text{C}$ ($-423\text{ }^{\circ}\text{F}$) are higher than these properties at $-195.5\text{ }^{\circ}\text{C}$ ($-320\text{ }^{\circ}\text{F}$). The ultimate tensile and yield strengths at $-195.5\text{ }^{\circ}\text{C}$ ($-320\text{ }^{\circ}\text{F}$) are higher than these properties at $21\text{ }^{\circ}\text{C}$ ($70\text{ }^{\circ}\text{F}$). The elongations at $-252.8\text{ }^{\circ}\text{C}$ ($-423\text{ }^{\circ}\text{F}$) and $-195.5\text{ }^{\circ}\text{C}$ ($-320\text{ }^{\circ}\text{F}$) are lower than the elongation at room temperature.

REFERENCES

1. Parsonage, T.B: “Use of Aluminum Beryllium for Structural Applications,” SPIE Conference Proceedings—Advanced Materials for Optics and Precision Structures, Vol. CR67, Paper CR67–14, 1997.
2. “Aluminum-Beryllium Alloy, Extrusions,” *SAE AMS7912*, Society of Automotive Engineers International, Warrendale, PA.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operation and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503				
1. AGENCY USE ONLY (Leave Blank)		2. REPORT DATE October 2002		3. REPORT TYPE AND DATES COVERED Technical Memorandum
4. TITLE AND SUBTITLE The Cryogenic Tensile Properties of an Extruded Aluminum-Beryllium Alloy			5. FUNDING NUMBERS	
6. AUTHORS W.R. Gamwell				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) George C. Marshall Space Flight Center Marshall Space Flight Center, AL 35812			8. PERFORMING ORGANIZATION REPORT NUMBER M-1059	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration Washington, DC 20546-0001			10. SPONSORING/MONITORING AGENCY REPORT NUMBER NASA/TM-2002-212049	
11. SUPPLEMENTARY NOTES Prepared by the Materials, Processes, and Manufacturing Department, Engineering Directorate				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Unclassified-Unlimited Subject Category 26 Nonstandard Distribution			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Basic mechanical properties; i.e., ultimate tensile strength, yield strength, percent elongation, and elastic modulus, were obtained for the aluminum-beryllium alloy, AlBeMet162, at cryogenic (-195.5 °C (-320 °F) and -252.8 °C (-423 °F)) temperatures. The material evaluated was purchased to the requirements of SAE-AMS7912, "Aluminum-Beryllium Alloy, Extrusions."				
14. SUBJECT TERMS AlBeMet162, tensile properties, extrusions, cryogenic			15. NUMBER OF PAGES 24	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT Unlimited	